



Frontlit coated Superflex SFL-FL-C-45.1010.1818
450 gsm 1000 x 1000 18 x 18

Declaration : Please choose products suitably according to relative provisions or industrial standards. We bear the responsibility for the specified technical and performance data on this page only. We are not responsible for any other liability. (The technical data on this page is calculated on average, and $\pm 5\%$ tolerance is acceptable.)

Description of commodity: SFL-FL-C-45.1010.1818 coated frontlit 1000D*1000D 18*18 450gsm			
ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100%PES(1000D)		DIN EN ISO2060
Construction	Weaving 18*18	inch	DIN60001
Total weight	450	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	155	g/sq.m	DIN53352 BS3424 method5B
Weight of pvc coating	295	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp : 2100	N/5cm	DIN53354 BS3424 method6A
	Weft : 1800		
Tearing strength	Warp : 290	N	DIN53356 BS3424 method 7A
	Weft : 240		
Adhesion	80	N/5cm	DIN53357 BS3425 method9B
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424 method10