



Mesh coated Superflex SFL-MSH-C-27.1010.99

270 gsm 1000 x 1000 9 x 9

Declaration : Please choose products suitably according to relative provisions or industrial standards. We bear the responsibility for the specified technical and performance data on this page only. We are not responsible for any other liability. (The technical data on this page is calculated on average, and $\pm 5\%$ tolerance is acceptable.)

Description of commodity: SFL-MSH-C-27.1010.99 coated mesh 1000D*1000D 9*9 270gsm			
ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100%PES(1000D*1000D)		DIN EN ISO2060
Construction	Weaving 9*9	inch	DIN60001
Total weight	270	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	100	g/sq.m	DIN53352 BS3424 method5B
Weight of PVC	170	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp : 850	N/5cm	DIN53354 BS3424 method6A
	Weft : 750		
Tearing strength	Warp : 185	N	DIN53356 BS3424 method 7A
	Weft : 155		
Suitable temperature	-20 -----+70	°C	DIN 53372 BS3424 method10